



## 565 UV MASKING TAPE



### Technical data sheet

#### Description

A blue crepe paper coated with modified acrylic adhesive and special formulation for UV resistance, specifically designed for outdoor painting or any paint job that requires clean removal after several days.

CONSTRUCTION	Backing	Adhesive	Core
	Crepe Paper	Natural rubber Synthetic Resins Plasticizers Antioxidants	Fiberboard

TECHNICAL SPECIFICATIONS		English System	International System	Procedures
	Total Thickness	4.9 mils	0.125 mm	PSTC-133
	Adhesion to Steel	21 oz/in	6.0 N/cm (240 gr-f/cm)	PSTC-101
	Elongation at break	11%	11%	PSTC-131
	Tensile Strength	24.6 lb/in	108 N/cm (4.4 kg-f/cm)	PSTC-131
	Temperature Resistance (30 min)	up to 230° F	up to 95° C	
Color	Blue			

AVAILABLE SIZES	Lengths	55 (yd)**	50 (m)
	Widths	3/4, 1 (in)**	18, 24 (mm)

\*\* Approximate (English) measure

APPLICATIONS / FEATURES	Pegafan 565 is used primarily for outdoor painting and provides clean removal after 14 days. It provides good conformability and mechanical resistance, and without adhesive transfer at slightly higher temperatures (95°C for 30 minute cycles). It performs well for achieving straight lines or color changes and designs.
-------------------------	--

STATEMENT OF PRACTICAL USE	Tape must be applied over surfaces which are clean, dry surface and free of grease, oil or other contaminants. After application, even pressure must be applied in order to activate the adhesive.
----------------------------	--

STORAGE CONDITIONS	It must be stored in its original packaging, in a well ventilated, low humidity area at temperatures between 15-25°C, away from direct sunlight.
--------------------	--

PLEASE NOTE	This information is based on laboratory tests conducted according to Test Methods for Pressure Sensitive Tapes (15th Edition) validated by the Pressure Sensitive Tape Council. For special applications, we recommend testing the suitability of the self adhesive tape for the designated application or use  * These tests were performed in a laboratory stove on metal surfaces.
-------------	---

March 2021

